

**NATA Accredited Laboratory** 

Accreditation No: 15305



Accredited for compliance with ISO/IEC 17025 - Testing

## The Laminex Group Technology Centre

Postal Address: PO BOX 720, Wendouree, Vic 3355 Address: 22 Trewin St, Wendouree, Vic 3355 Telephone: (03) 5337 3613 Fax: (03) 5337 3647

## Test Report No. 2331242

Date of Issue 24/07/23

Client:

Laminex New Zealand - Technical Services 810 Great South Road, Penrose, Auckland 1061, New Zealand

This test report shall not be reproduced, except in full, without written approval from The Laminex Group Technology Centre

The material contained is this report is confidential to the entity identified as 'Client' above.

As the sample(s) have been provided by the cleint, the results contained in this report apply only to the sample(s) as received.

Test Report No. 2331242 Date of Issue: 24/07/23

Laminex Sample Reference No.	31242		
Client Sample Reference No.	Melteca FR MDF		
Product Description:			
(Supplied by client)	Melteca decorated FR MDF		
Surface Treatment	Low Pressure Melamine (LPM)		
Receive Date:	27/06/23		
Condition:	Good		
Testing Performed Date(s):	21/07/23		
Specification Standard	AS/NZS 1859.2:2017		
Product Classification	>12 to 22mm Medium Density Fibreboard		

Test Report No. 2331242 Date of Issue: 24/07/23

MDF					
Test	Method	Unit	Mean	STD Dev	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.33	0.02	

2						7
C	O	m	m	e	n	ES

Test sample meets E0 formaldehyde classification.

Approved Signatory: